

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

Patent Abstracts of Japan

PUBLICATION NUMBER : 08146201
PUBLICATION DATE : 07-06-96

APPLICATION DATE : 24-11-94
APPLICATION NUMBER : 06289395

APPLICANT : OLYMPUS OPTICAL CO LTD;

INVENTOR : KAWAMATA TAKESHI;

INT.CL. : G02B 1/10 C30B 25/06

TITLE : PRODUCTION OF OPTICAL THIN FILM

ABSTRACT : PURPOSE: To produce an optical thin film of high quality at a low cost by using a single crystal Si target to produce the thin film.

CONSTITUTION: In the production process of an optical thin film, a single crystal Si target is used to form a SiO₂ film by reactive sputtering in the environment into which at least two kinds of gases of a gas containing oxygen and an inert gas are introduced while impressing pulses of positive voltage on a DC power source. In this method, the resistance of the single crystal Si target is specified to $\leq 10\text{m}\Omega\cdot\text{cm}$. By this method, since no intergranular interface is present in the crystal different from a polycrystalline target, the surface roughness of the target is not increased. Therefore, arc discharge is hardly caused. The target has excellent uniformity in the target surface, and as a result, even when a film is formed on a large substrate, the film quality shows higher uniformity. By impressing pulses of positive voltage on the DC power source, charges hardly accumulate on the surface of the target.

COPYRIGHT: (C)1996,JPO